

KIMMARK (M) SDN BHD (CO.NO.328613-D)

LOT 1808, JALAN KPB 3,
KAWASAN PERINDUSTRIAN KG. BARU BALAKONG,
43300, SERI KEMBANGAN, SELANGOR DARUL EHSAN, MALAYSIA.
TEL: +603-8961 8998, 8961 9098, 8961 0098, 8962 2890, 8962 6708
FAX: +603-8961 0998 and +603-8961 6998

Website: www.kimmark.com

Email: sales@kimmark.com

LE MERIDIAN LEATHER SPECIFICATION SHEET

Thickness: 1.1/1.3mm

Description: Semi Aniline

Cleaning:

Problems	Tips
Dust	Remove gently with a clean soft cloth.
Dried on dirt	Use dampened soft cloth, wipe away gently without rubbing the stain rigorously, then allow it to dry then apply special care agent
Liquid	Dap immediately with a dry absorbent cloth, do not rub, follow the tips for dried on dirt
Food & Grease	Remove immediately just like dried on dirt, in most cases grease marks will disappear in time.
Wax (polish)	Placing blotting paper on the leather and applying a cool/moderate iron. Keep applying the iron on clean blotting paper to the wax spot until the paper is no longer absorbing the wax.
Scratch marks	Applying a shoe renovating polish or marker pen

No	Properties	Specification	Unit	Method
1	Tear Resistance	Min 30	N	ISO 3377-1
2	Light Fastness	Min 3	Blue Scale	ISO 105-B02
3	Resistance to Rubbing (Dry)	300 Cycles Min Grade 4	Grey Scale	ISO 11640
4	Resistance to Rubbing (Wet)	150 Cycles Min 3/4	Grey Scale	ISO 11640
5	Resistance to Rubbing (Perspiration)	50 Cycles Min 3/4	Grey Scale	ISO 11640
6	Finish Adhesion	Min 3	N/cm	ISO 11644
7	Flexing Endurance	25.000 Cycles - No cracks visible with 6X magnifying glass	-	ISO 5402
8	pH	Min 3.5 - If the pH value is below 4, ΔpH 0.7	-	ISO 4045
9	Δ pH			